

# ULTEM™ 1010 resin

聚醚酰亚胺

SABIC Innovative Plastics



ides.com/prospector

## Technical Data

### 产品说明

Transparent, enhanced flow Polyetherimide (Tg 217°C). ECO Conforming, UL94 V0 and 5VA listing. US FDA and EU Food Contact compliant, NSF 51 listing. Effective June 2007, this grade will no longer be supported with biocompatibility information and should not be used for medical applications which require biocompatibility. Alternative grade HU1010.

### 总体

材料状态	• 已商用 : 当前有效
资料 <sup>1</sup>	• <a href="#">Technical Datasheet</a>
UL 黄卡 <sup>2</sup>	• <a href="#">E121562-101048269</a>
搜索 UL 黄卡	• <a href="#">SABIC Innovative Plastics</a> • <a href="#">ULTEM™</a>
供货地区	• 北美洲
性能特点	• 符合 ECO • 良好的流动性 • 食品接触的合规性
机构评级	• EU Eco • NSF 51 • FDA 食品接触, 未评级 • 欧洲 食品接触, 未评级
外观	• 清晰/透明
加工方法	• 注射成型

- 多点数据
- Coefficient of Thermal Expansion vs. Temperature (ASTM E831)
  - Flexural DMA (ASTM D4065)
  - Instrumented Impact (Energy) (ASTM D3763)
  - Instrumented Impact (Load) (ASTM D3763)
  - Pressure-Volume-Temperature (PVT - Zoller Method)
  - Shear DMA (ASTM D4065)
  - Specific Heat vs. Temperature (ASTM D3417)
  - Tensile Creep (ASTM D2990)
  - Tensile Fatigue
  - Tensile Stress vs. Strain (ASTM D638)
  - Thermal Conductivity vs. Temperature (ASTM E1530)
  - Viscosity vs. Shear Rate (ASTM D3835)

物理性能	额定值 单位制	测试方法
比重	1.27 g/cm <sup>3</sup>	ASTM D792
熔流率 (337°C/6.6 kg)	18 g/10 min	ASTM D1238
收缩率 - 流动 (3.20 mm)	0.50 到 0.70 %	Internal Method
吸水率		ASTM D570
24 hr	0.25 %	
平衡, 23°C	1.3 %	

机械性能	额定值 单位制	测试方法
拉伸模量 <sup>4</sup>	3590 MPa	ASTM D638
抗张强度 <sup>5</sup> (屈服)	110 MPa	ASTM D638
伸长率 <sup>5</sup>		ASTM D638
屈服	7.0 %	
断裂	60 %	
弯曲模量 <sup>6</sup> (100 mm 跨距)	3520 MPa	ASTM D790
弯曲强度 <sup>6</sup> (屈服, 100 mm 跨距)	165 MPa	ASTM D790
抗泰伯磨损 (1000 Cycles, 1000 g, CS-17 转轮)	10.0 mg	ASTM D1044

冲击性能	额定值 单位制	测试方法
悬臂梁缺口冲击强度 (23°C)	32 J/m	ASTM D256
无缺口悬臂梁冲击 (23°C)	1300 J/m	ASTM D4812
反向缺口冲击 (3.20 mm)	1200 J/m	ASTM D256
落锤冲击 (23°C)	33.9 J	ASTM D3029

# ULTEM™ 1010 resin

聚醚酰亚胺

SABIC Innovative Plastics



ides.com/prospector

硬度	额定值 单位制	测试方法
洛氏硬度 (M 计秤)	109	ASTM D785
热性能	额定值 单位制	测试方法
热变形温度		ASTM D648
0.45 MPa, 未退火, 6.40 mm	207 °C	
1.8 MPa, 未退火, 6.40 mm	199 °C	
维卡软化温度	219 °C	ASTM D1525 <sup>7</sup>
线形膨胀系数 - 流动 (-20 到 150°C)	0.000056 cm/cm/°C	ASTM E831
导热系数	0.22 W/m/K	ASTM C177
RTI Elec	170 °C	UL 746
RTI Imp	170 °C	UL 746
RTI Str	170 °C	UL 746
电气性能	额定值 单位制	测试方法
体积电阻率	1.0E+17 ohm·cm	ASTM D257
介电强度		ASTM D149
1.60 mm, in Air	33 kV/mm	
1.60 mm, in Oil	28 kV/mm	
介电常数 (1 kHz)	3.15	ASTM D150
耗散因数		ASTM D150
1 kHz	0.0013	
2.45 GHz	0.0025	
耐电弧性 <sup>8</sup>	PLC 5	ASTM D495
相比耐漏电起痕指数(CTI)	PLC 4	UL 746
高电弧燃烧指数(HAI)	PLC 3	UL 746
高电压电弧起痕速率 (HVTR)	PLC 2	UL 746
热丝引燃 (HWI)	PLC 1	UL 746
可燃性	额定值 单位制	测试方法
UL 阻燃等级		UL 94
0.750 mm	V-0	
3.00 mm	5VA	
极限氧指数	44 %	ASTM D2863
NBS Smoke Density - Flaming, Ds, 4 min	2.00	ASTM E662
注射	额定值 单位制	
干燥温度	149 °C	
干燥时间	4.0 到 6.0 hr	
干燥时间, 最大	24 hr	
建议的最大水分含量	0.020 %	
建议注入量	40 到 60 %	
螺筒后部温度	332 到 399 °C	
螺筒中部温度	338 到 399 °C	
螺筒前部温度	343 到 399 °C	
射嘴温度	343 到 399 °C	
加工 (熔体) 温度	349 到 399 °C	
模具温度	135 到 163 °C	
背压	0.345 到 0.689 MPa	
螺杆转速	40 到 70 rpm	
排气孔深度	0.025 到 0.076 mm	

备注

<sup>1</sup> 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

<sup>2</sup> UL 黄卡含有 UL 验证的易燃性和电气特性。UL IDES 持续努力在 Prospector 中将黄卡链接至单个塑料材料，然而此列表可能未包括所有相应链接。重要的是，我们对 Prospector 中找到的这些黄卡和塑料材料之间的关联进行验证。如需完整的黄卡列表，请访问 UL 黄卡搜索。

<sup>3</sup> 一般属性：这些不能被视为规格。

<sup>4</sup> 5.0 mm/min

<sup>5</sup> 类型 1, 5.0 mm/min

<sup>6</sup> 2.6 mm/min

<sup>7</sup> 标准 B (120°C/h), 压力 2 (50N)

<sup>8</sup> 钨电极

# ULTEM™ 1010 resin

聚醚酰亚胺

SABIC Innovative Plastics

## 购买地点

### 供应商

**SABIC Innovative Plastics**  
Pittsfield, MA USA  
电话: 800-845-0600  
Web: <http://www.sabic-ip.com/>

### 分销商

**Nexeo Solutions**  
电话: 800-531-7106  
Web: <http://www.nexeosolutions.com/>  
可用性: North America



Founded in 1986 and based in Laramie, Wyoming, IDES is now part of the UL family of companies. UL is a premier global independent safety science company with more than a century of proven history. Employing nearly 10,000 professionals in over 100 countries, UL has five distinct business units -- Product Safety, Environment, Life & Health, Knowledge Services and Verification Services -- to meet the expanding needs of our customers and to deliver on our public safety mission.



### Prospector Plastics Database - [www.ides.com/prospector](http://www.ides.com/prospector)

Prospector is a searchable online database that includes 85,000 data sheets from 875 manufacturers and 44,000 UL yellow cards. Each data sheet includes property, processing and supplier contact information. Prospector is relied on by nearly 400,000 design engineers and plastics processors. Using Prospector, they save time with plastic material selection by quickly and easily referencing technical information critical to the success of their products.

"Prospector is absolutely the best and most well-known search engine for plastic raw materials in the world. We use Prospector every day – it's a real time saver!"

– Birgit Elvardt Bader, Production Manager, Micoctron

#### Power Searches

**Property Search** – select plastics by 500 key properties and design parameters.

**Alternative Resins Search** – find replacement plastics within minutes.

**Automotive Plastics Search** – easily locate automotive approved plastics.

**Curve Data** – view, overlay and export curve data.



### Material Data Management – [www.ides.com/datasheets](http://www.ides.com/datasheets)

With our data management services, plastic suppliers and distributors can have custom search interfaces available on their website for their customers, website visitors, sales and customer service teams. These provide intuitive ways to find and view technical data sheets for their products.

"With UL IDES data services, our website now displays the most current information on the products we distribute and links to our backend RFQ and sales order system, adding both value and service for our customers."

– Kevin Chase, Owner & President, Chase Plastics



### Advertising – [www.ides.com/advertise](http://www.ides.com/advertise)

Reach 365,000 pre-qualified plastics professionals and generate leads with proven techniques. Electronic newsletter insertions, sponsored webinars and powerful online ads are available to make the most of your lead-generation program.

For more information, call: 800.788.4668 or 307.742.9227 ext. 220